

Abstract Submitted to the
International Conference on Strongly Correlated Electron Systems
University of Michigan, Ann Arbor
August 6-10, 2001

**Anisotropic strains, metal-insulator transition, and magnetoresistance
of $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ films**

J. H. Song, J. H. Park, Y. H. Jeong

*Department of Physics and electron Spin Science Center, Pohang University of Science and
Technology, Pohang, S. Korea*

Thin films of perovskite manganite $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ were grown epitaxially on $\text{SrTiO}_3(100)$, $\text{MgO}(100)$ and $\text{LaAlO}_3(100)$ substrates by the Laser Molecular Beam Epitaxy. Microscopic structures of these thin film samples were determined by x-ray diffraction measurements. The unit cells of these films have different shapes, i.e., contracted tetragonal, cubic, and elongated tetragonal for SrTiO_3 , MgO , and LaAlO_3 cases, respectively, while the unit cell of the bulk is cubic. In addition, the transition temperature of the metal-insulator transition depends sensitively on the strain in the lattice. It is found that the samples with cubic unit cell show smaller peak magnetoresistance at low fields ($\lesssim 1$ T) than the noncubic ones do. The present result demonstrates that the magnetoresistance of $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ at low fields is sensitive to the strain effects and therefore can be controlled by lattice distortion via externally imposed strains [1]. The underlying physics will be discussed in terms of the Jahn-Teller effect.

[1] T. Y. Koo, S. H. Park, K. -B. Lee, Y. H. Jeong, Appl. Phys. Lett. 71, 977 (1997)